

FORM PTO-1390 (REV. 11-2000)		U.S. DEPARTMENT OF COMMERCE PATENT AND TRADEMARK OFFICE		ATTORNEY'S DOCKET NUMBER	
TRANSMITTAL LETTER TO THE UNITED STATES DESIGNATED/ELECTED OFFICE (DO/EO/US) CONCERNING A FILING UNDER 35 U.S.C. 371				1752-0155P	
				U.S. APPLICATION NO. (If known, see 37 CFR 1.5) 10/049517	
INTERNATIONAL APPLICATION NO. PCT/Jp00/05881		INTERNATIONAL FILING DATE August 30, 2000		PRIORITY DATE CLAIMED August 31, 1999	
TITLE OF INVENTION AROMATIC OLIGOMER AND USE THEREOF					
APPLICANT(S) FOR DO/EO/US SENZAKI, Toshihide; IMAMURA, Takahiro					
Applicant herewith submits to the United States Designated/Elected Office (DO/EO/US) the following items and other information:					
<ol style="list-style-type: none"> 1. <input checked="" type="checkbox"/> This is a FIRST submission of items concerning a filing under 35 U.S.C. 371. 2. <input type="checkbox"/> This is a SECOND or SUBSEQUENT submission of items concerning a filing under 35 U.S.C. 371. 3. <input checked="" type="checkbox"/> This express request to begin national examination procedures (35 U.S.C. 371(f)) at any time rather than delay examination until the expiration of the applicable time limit set in 35 U.S.C. 371(b) and PCT Articles 22 and 39 (1). 4. <input checked="" type="checkbox"/> The US has been elected by the expiration of 19 months from the priority date (Article 31). 5. <input checked="" type="checkbox"/> A copy of the International Application as filed (35 U.S.C. 371(c)(2)) <ol style="list-style-type: none"> a. <input type="checkbox"/> is transmitted herewith (required only if not transmitted by the International Bureau). b. <input checked="" type="checkbox"/> has been transmitted by the International Bureau. WO 01/16199 c. <input type="checkbox"/> is not required, as the application was filed in the United States Receiving Office (RO/US). 6. <input checked="" type="checkbox"/> An English language translation of the International Application as filed (35 U.S.C. 371(c)(2)). <ol style="list-style-type: none"> a. <input checked="" type="checkbox"/> is transmitted herewith. b. <input type="checkbox"/> has been previously submitted under 35 U.S.C. 154(d)(4) 7. <input checked="" type="checkbox"/> Amendments to the claims of the International Application under PCT Article 19 (35 U.S.C. 371(c)(3)). <ol style="list-style-type: none"> a. <input type="checkbox"/> are transmitted herewith (required only if not transmitted by the International Bureau). b. <input type="checkbox"/> have been transmitted by the International Bureau. c. <input type="checkbox"/> have not been made; however, the time limit for making such amendments has NOT expired. d. <input checked="" type="checkbox"/> have not been made and will not be made. 8. <input type="checkbox"/> An English language translation of the amendments to the claims under PCT Article 19 (35 U.S.C. 371(c)(3)). 9. <input type="checkbox"/> An oath or declaration of the inventor(s) (35 U.S.C. 371(c)(4)). 10. <input type="checkbox"/> An English language translation of the annexes of the International Preliminary Examination Report under PCT Article 36 (35 U.S.C. 371(c)(5)). 					
Items 11. to 20. below concern document(s) or information included:					
<ol style="list-style-type: none"> 11. <input checked="" type="checkbox"/> An Information Disclosure Statement under 37 CFR 1.97 and 1.98, Form PTO-1449(s), and International Search Report (PCT/ISA/210) with 0 cited document(s). 12. <input type="checkbox"/> An assignment document for recording. A separate cover sheet in compliance with 37 CFR 3.28 and 3.31 is included. 13. <input checked="" type="checkbox"/> A FIRST preliminary amendment. 14. <input type="checkbox"/> A SECOND or SUBSEQUENT preliminary amendment. 15. <input type="checkbox"/> A substitute specification. 16. <input type="checkbox"/> A change of power of attorney and/or address letter. 17. <input type="checkbox"/> A computer-readable form of the sequence listing in accordance with PCT Rule 13ter.2 and 35 U.S.C. 1.821-1.825. 18. <input type="checkbox"/> A second copy of the published international application under 35 U.S.C. 154(d)(4). 19. <input type="checkbox"/> A second copy of the English language translation of the international application under 35 U.S.C. 154(d)(4). 20. <input checked="" type="checkbox"/> Other items or information: <ol style="list-style-type: none"> 1.) Verification of Translation 2.) PCT/IB/304 and PCT/IB/308 3.) Two (2) sheets of Formal Drawings 					

JC12 Rec'd PCT/PTO 13 FEB 2002

U.S. APPLICATION NO (if known, see 37 CFR 1.5) 10/049517		INTERNATIONAL APPLICATION NO PCT/Jp00/05881		ATTORNEY'S DOCKET NUMBER 1752-0155P	
--------------------------------------------------------------------	--	------------------------------------------------	--	----------------------------------------	--

21. <input checked="" type="checkbox"/> The following fees are submitted: BASIC NATIONAL FEE (37 CFR 1.492(a)(1)-(5): Neither international preliminary examination fee (37 CFR 1.482) nor international search fee (37 CFR 1.445(a)(2)) paid to USPTO and International Search Report not prepared by the EPO or JPO. \$1,040.00 International preliminary examination fee (37 CFR 1.482) not paid to USPTO but International Search Report prepared by the EPO or JPO \$890.00 International preliminary examination fee (37 CFR 1.482) not paid to USPTO but international search fee (37 CFR 1.445(a)(2)) paid to USPTO. \$740.00 International preliminary examination fee (37 CFR 1.482) paid to USPTO but all claims did not satisfy provisions of PCT Article 33(1)-(4) \$710.00 International preliminary examination fee (37 CFR 1.482) paid to USPTO and all claims satisfied provisions of PCT Article 33(1)-(4). \$100.00 ENTER APPROPRIATE BASIC FEE AMOUNT =				CALCULATIONS PTO USE ONLY	
				\$	890.00
Surcharge of \$130.00 for furnishing the oath or declaration later than <input type="checkbox"/> 20 <input checked="" type="checkbox"/> 30 months from the earliest claimed priority date (37 CFR 1.492(e)).				\$	130.00
CLAIMS	NUMBER FILED	NUMBER EXTRA	RATE		
Total Claims	6 - 20 =	0	X \$18.00	\$	0
Independent Claims	1 - 3 =	0	X \$84.00	\$	0
MULTIPLE DEPENDENT CLAIM(S) (if applicable) None + \$280.00				\$	0
TOTAL OF ABOVE CALCULATIONS =				\$	1020.00
<input type="checkbox"/> Applicant claims small entity status. See 37 CFR 1.27. The fees indicated above are reduced by 1/2.				\$	0
SUBTOTAL =				\$	1020.00
Processing fee of \$130.00 for furnishing the English translation later than <input type="checkbox"/> 20 <input type="checkbox"/> 30 months from the earliest claimed priority date (37 CFR 1.492(f)).				\$	0
TOTAL NATIONAL FEE =				\$	1020.00
Fee for recording the enclosed assignment (37 CFR 1.21(h)). The assignment must be accompanied by an appropriate cover sheet (37 CFR 3.28, 3.31). \$40.00 per property +				\$	0
TOTAL FEES ENCLOSED =				\$	1020.00
				Amount to be:	
				refunded	\$
				charged	\$

a. ☒ A check in the amount of \$ **1020.00** to cover the above fees is enclosed.


b. ☐ Please charge my Deposit Account. No. _____ in the amount of \$ _____ to cover the above fees.
 A duplicate copy of this sheet is enclosed.

c. ☒ The Commissioner is hereby authorized to charge any additional fees which may be required, or credit any
 overpayment to Deposit Account No. 02-2448.

NOTE: Where an appropriate time limit under 37 CFR 1.494 or 1.495 has not been met, a petition to revive (37 CFR 1.137(a) or (b)) must be filed and granted to restore the application to pending status.

Send all correspondence to
Birch, Stewart, Kolasch & Birch, LLP or Customer No. 2292
P.O. Box 747
Falls Church, VA 22040-0747
(703) 205-8000

Date: February 13, 2002


 Gerald M. Murphy, Jr., #28,977
 32,181

1004951710/049517

JC13 Rec'd PCT/PTO 13 FEB 2002

IN THE UNITED STATES PATENT AND TRADEMARK OFFICE

In re International Application of

Toshihide SENZAKI et al.

International Serial No. : PCT/JP00/05881

International filing date : August 30, 2000

For : Aromatic Oligomer and Use Thereof

VERIFICATION OF TRANSLATION

Honorable Commissioner of Patents and Trademarks

Washington, D.C. 20231

Sir :

I, Nobuyoshi TAKAHASHI, residing at 504-52, Shimoyamaguchi, Hayama-machi, Miura-gun, Kanagawa-ken, Japan, declare and state :

- (1) that I know well both the Japanese and English languages;
- (2) that I translated the above-identified International Application from Japanese to English;
- (3) that the attached English translation is a true and correct translation of the above-identified International Application to the best of my knowledge and belief and
- (4) that all statements made of my own knowledge are true and that all statements made on information and belief are believed to be true, and further that these statements are made with the knowledge that willful false statements and the like are punishable by fine or imprisonment, or both, under 18 USC 1001, and that such false statements may jeopardize the validity of the application or any patent issuing thereon.

Date : January 8, 2002

Nobuyoshi Takahashi
Signature: Nobuyoshi TAKAHASHI

PATENT
1752-0155P

IN THE U.S. PATENT AND TRADEMARK OFFICE

Applicant: SENZAKI, Toshihide et al.
Int'l. Appl. No.: PCT/JP00/05881
Appl. No.: New Group:
Filed: February 13, 2002 Examiner:
For: AROMATIC OLIGOMER AND USE THEREOF

PRELIMINARY AMENDMENT

BOX PATENT APPLICATION

Assistant Commissioner for Patents
Washington, DC 20231

February 13, 2002

Sir:

The following Preliminary Amendments and Remarks are respectfully submitted in connection with the above-identified application.

AMENDMENTS

IN THE SPECIFICATION:

Please amend the specification as follows:

Before line 1, insert --This application is the national phase under 35 U.S.C. § 371 of PCT International Application No. PCT/JP00/05881 which has an International filing date of August 30, 2000, which designated the United States of America.--

Docket No. 1752-0155P

REMARKS


The specification has been amended to provide a cross-reference to the previously filed International Application.

Entry of the above amendments is earnestly solicited. An early and favorable first action on the merits is earnestly solicited.

If necessary, the Commissioner is hereby authorized in this, concurrent, and future replies, to charge payment or credit any overpayment to Deposit Account No. 02-2448 for any additional fees required under 37 C.F.R. § 1.16 or under 37 C.F.R. § 1.17; particularly, extension of time fees.

Respectfully submitted,

BIRCH, STEWART, KOLASCH & BIRCH, LLP

By 
Gerald M. Murphy, Jr. #28,977
32,181

GMM/cgc
1752-0155P

P.O. Box 747
Falls Church, VA 22040-0747
(703) 205-8000

(Rev. 11/13/01)

2/p₁

SPECIFICATION

Title of the Invention

Aromatic Oligomer and Use Thereof

Field of Technology

This invention relates to aromatic oligomers and uses thereof. The aromatic oligomers of this invention are useful as tackifiers to provide adhesive properties and incorporated in resins and rubbers in formulating adhesives, pressure sensitive adhesives and coatings. Moreover, the oligomers of this invention are useful as vibration damping agents effective in the range from room temperature to about 170 °C and incorporated in resins and rubbers for use in the industrial sectors that may cause problems relating to vibration and noise such as construction materials, electrical appliances, automobiles, bridges, motors, power generators and engines.

Background Technology

Resins obtained by the reaction of phenols with formaldehyde compound in the presence of an acid catalyst are well known as phenolic resins or novolak resins. Likewise, resins obtained by the reaction of aromatic hydrocarbons such as xylene with formaldehyde compound in the presence of an acid catalyst are well known as hydrocarbon resins. Indene-cumarone resins and petroleum resins are also known as hydrocarbon resins; in this case, however, indene, cumarone and cyclopentadiene themselves possess olefinic bonds and formaldehyde compound is not used in the reaction.

The use of resin obtained by the reaction of an aromatic oil with formaldehyde compound in the presence of an acid catalyst as an ingredient in formulating coatings is described in Japanese patent publication JP53-24973 B(1978). Resin compositions formulated by incorporating naphthalene, methylnaphthalene and acenaphthene in phenolic resins are described in JP59-52887 B(1984), JP07-242719 A(1995) and JP08-157571 A(1996).

Tackifiers are often added to a variety of adhesives such as hot-melt adhesives, emulsion adhesives and pressure sensitive adhesives in order to

improve the adhesive strength and raise the initial adhesive strength. For example, JP10-195047 A(1998) teaches the addition of a variety of tackifier resins to acrylic emulsion adhesives. JP10-158626 A(1998) and JP06-145626 A(1994) also teach the addition of a variety of tackifier resins to hot-melt adhesives derived from SBR-based block copolymers or modifications thereof by hydrogenation or epoxidation. Furthermore, W095-12623 teaches the addition of a variety of tackifier resins to acrylic pressure sensitive adhesives. The aforementioned patents describe a relatively large number of tackifiers in common; for example, indene-cumarone resins, petroleum resins, rosin-derived resins, xylene resins, phenolic resins, terpene resins and styrene resins. These tackifier resins are suitably chosen in consideration of such factors as compatibility with the base resin or rubber, use conditions such as temperature and presence or absence of solvents. As for their performance, there are demands for improved adhesive strength and improved initial adhesive strength and, additionally, suppressed generation of an offensive odor at use temperature and low price in the case of hot-melt adhesives.

A number of methods have been proposed for controlling vibration damping properties by the use of petroleum resins: for example, the use of commercially available petroleum resins and cumarone-indene resins reported in JP63-11980 A(1988) and JP62-141069 A(1987) and the use of commercially available polybutenes, terpene resins or modified rosin reported in JP02-49063 A(1990). The use of alkylbenzene-methylnaphthalene resins as an example of polycyclic aromatic resins is described in JP07-90130 A(1995).


A vibration damping agent to be incorporated in a base material such as rubber, resin and bitumen to improve vibration damping properties must desirably satisfy the following properties; the loss factor ($\tan \delta$) of a vibration damping material in which the agent in question is incorporated is large in the use region and the temperature dependency of $\tan \delta$ is small. It is known, however, that these properties are often contrary to each other.

An object of this invention is to provide a novel aromatic oligomer which emits little or no odor. Another object of this invention is to provide a vibration damping agent which can be readily obtained. A further object of this invention is to provide a polycyclic vibration damping agent manifesting a high degree of vibration damping performance. A still further object of this invention is to provide a vibration damping agent which manifests excellent

vibration damping performance in a wide temperature range.

Disclosure of the Invention

This invention relates to an aromatic oligomer which is represented by the following formula (1);



wherein A is a unit comprising (a) 30-90 wt% of an aromatic compound containing 2-4 rings and (b) 10-70 wt% of a phenol compound, F is methylene or a mixture of methylene and $-CH_2OCH_2-$ and n is a number of 1-100.

This invention also relates to said aromatic oligomer wherein the oxygen content is 20% or less. Moreover, this invention relates to an aromatic oligomer resin which comprises said aromatic oligomer as the principal component.

Still more, this invention relates to said aromatic oligomer or said aromatic oligomer resin which is obtained by the reaction of 1 kind or 2 kinds or more of aromatic compounds selected from naphthalene, methylnaphthalene, dimethylnaphthalene, acenaphthene, fluorene, anthracene, phenanthrene, pyrene, benzothiophene and fluoranthene with 1 kind or 2 kinds or more of phenols selected from phenol and alkylphenols and 1 kind or 2 kinds or more of formaldehyde compound selected from formalin, formaldehyde and paraformaldehyde and exhibits a softening point of 50-180°C.

Also, this invention relates to a tackifier or a vibration damping agent comprising said aromatic oligomer or aromatic oligomer resin as an active ingredient.

Explanation will be given below to the method for preparing the aromatic oligomer or the aromatic oligomer resin which comprises said aromatic oligomer as the principal component and, at the same time, explanation will be given to the invention of the aromatic oligomer. It is to be noted that the aromatic oligomer to be obtained in accordance with the method of this invention is generally a mixture unless pure raw materials are used and may contain a resin which cannot be represented by general formula (1); however, the aromatic oligomer in question contains 50% or more, preferably 80% or more, of the resin represented by general formula (1) as the principal component. In this specification, % in respect to purity or concentration signifies wt % unless otherwise specified. The components in the aromatic oligomer actually mean the unit or radical derived from monomers such as an aromatic compound and a phenol

existing in the oligomer; for the simplicity of explanation, however, the unit or radical present in the oligomer may often be simply described by the name of the monomer. The aromatic oligomer resin means a resin which comprises the aforementioned aromatic oligomer as the principal component, that is, in an amount of 50% or more, preferably 70% or more, more preferably 80% or more. It is to be understood here, for the simplicity of explanation, that "the aromatic oligomer" refers not only to the aromatic oligomer but also to the aromatic oligomer resin which comprises the aromatic oligomer as the principal component unless it makes a contradictory statement.

A compound useful for the aromatic compound is preferably the one that boils higher than naphthalene or a mixture of such compounds. Concretely, it is an aromatic compound consisting of an aromatic ring linked to one or more rings, the aromatic ring here being selected from 5- or 6-membered rings consisting entirely of carbon atoms, 5- or 6-membered rings consisting of one oxygen atom and carbon atoms and 5- or 6-membered rings consisting of one sulfur atom and carbon atoms, and it is preferably an aromatic compound comprising condensed 2-4 aromatic rings. The aforementioned aromatic compound may be substituted with 1-5 alkyl groups, each alkyl group containing 8 carbon atoms or less.

Preferably, the aromatic compound is a polycyclic aromatic hydrocarbon; more preferably, it is naphthalene, methylnaphthalene, dimethylnaphthalene, acenaphthene, fluorene, anthracene, phenanthrene, pyrene or fluoranthene; and most preferably, it is naphthalene, methylnaphthalene or dimethylnaphthalene. In addition, benzothiophene may be cited as a preferable aromatic compound. It does not matter whether these aromatic hydrocarbons are materials of high purity or occur as the principal components in an aromatic oil such as aromatic hydrocarbon oil. Available as such aromatic hydrocarbon oil are the fractions corresponding to naphthalene oil, methylnaphthalene oil and middle oil and the intermediate products and the residual oil obtained by recovering the principal components from said fractions by such means as distillation.

The aromatic hydrocarbon oil should naturally comprise aromatic hydrocarbons as the principal components, but it may additionally contain hetero aromatic compounds having N, S, O and the like in the ring and aromatic compounds having functional groups containing such hetero atoms. Furthermore, it may contain inert aliphatic hydrocarbons. Preferably, the aromatic hydrocarbon oil contains 80% or more of bicyclic or tricyclic aromatic hydrocarbons with naphthalene or alkylnaphthalene accounting for 70% or more of said bicyclic or tricyclic

aromatic hydrocarbons. The unrefined aromatic hydrocarbon oil may contain phenols and, in such a case, the phenols contained are calculated as part of the whole phenols.

Formaldehyde compound useful for this invention is adequate if it generates formaldehyde in the reaction system and formaldehyde itself, formalin and paraformaldehyde can be used, paraformaldehyde being preferred.

Phenol compound useful for this invention include phenol, alkylphenols such as cresol, xlenol and tert-butylphenol, polyhydric phenols such as resorcin and pyrogallol and hydroxylated polycyclic aromatic compounds such as naphthol. Preferable from the standpoint of reactivity and properties of oligomer are monohydric phenols such as phenol and lower alkylphenols containing 6 carbon atoms or less in the alkyl group. Phenols are calculated not as the aromatic compound of this invention but as phenols.

The catalyst useful for this invention is an acid catalyst and its examples are inorganic acids such as sulfuric acid, phosphoric acid and hydrochloric acid, organic acids such as oxalic acid and toluenesulfonic acid and solid acids such as silica-alumina, zeolite, ion exchange resin and acid clay. Preferable among them are organic acids such as oxalic acid and toluenesulfonic acid. A thermally decomposable catalyst such as oxalic acid produces an extra effect that the step for its removal can be omitted.

The proportion of (a) an aromatic compound, (b) a phenol compound and (c) formaldehyde compound in use is as follows, although it varies more or less with the content of other aromatic compounds; the ratio $(c)/[(a) + (b)]$ by mole is 0.1-0.9, preferably 0.2-0.7, more preferably 0.4-0.7, wherein the number of moles of a derivative of formaldehyde, in case it is used, is calculated as that of formaldehyde generated from the derivative and the ratio $(b)/(a)$ by weight is 10/90 - 30/70-90, preferably 30/70 - 50/50.

Formaldehyde compound is needed to increase the molecular weight of the aromatic oligomer and to raise the conversion of naphthalene and other aromatic compounds. The use of too much formaldehyde furthers the possibility of gelation taking place or the terminal methylol groups remaining behind in large quantities. A phenol compound not only effectively increases the molecular weight of the aromatic oligomer but also performs the functions of providing suitable polarity and improving the adhesion to metallic materials; however, too

much phenols causes loss of characteristics as hydrocarbon resin. An aromatic compound performs the functions of controlling adequately the polarity of the aromatic oligomer and improving the compatibility with other resins such as SBR or with solvents.

The amount used of the acid catalyst is generally 0.5-20 wt% of the reactants, although it varies with the kind of acid catalyst, and it is preferably 5-10 wt% in the case of oxalic acid.

The reaction conditions vary with the raw materials and the catalyst to be used, but generally the reaction temperature is 50-180°C and the reaction time is 0.5-5 hours. Formaldehyde compound, an aromatic compound and a phenol participate in the reaction and, in case the phenol is present in a small amount or absent, the product is an oligomer such as hydrocarbon resin or phenol-modified hydrocarbon resin. In case the phenol is added in a large amount, the product is an oligomer such as hydrocarbon-modified novolak resin. A solvent may be used as needed.

Upon completion of the reaction, the reaction mixture is distilled to strip off low-boiling substances such as water and formaldehyde first, then the remaining mixture is heated under reduced pressure to 200-250-300°C to distill the unreacted raw materials and other fractions thereby leaving the aromatic oligomer as residue. When the reaction is over, the catalyst may be removed by such means as water washing if necessary and, in this case, the reaction terminates at this point. Without removal of the catalyst here, the reaction advances partly while the reaction mixture is being distilled. In case an oil containing naphthalene or methylnaphthalene is used in excess as an aromatic compound, the naphthalene fraction recovered as the unreacted raw material is crystallized or washed to obtain refined naphthalene. Likewise, the methylnaphthalene fraction yields refined methylnaphthalene.

The aromatic oligomer to be obtained in this manner is the oligomer represented by the aforementioned formula (1) or the aromatic oligomer resin which comprises said aromatic oligomer as the principal component. In formula (1), A is a segment mainly comprising (a) an alkyl-substituted or alkyl-unsubstituted bicyclic or tetracyclic aromatic compound and (b) a phenol at a ratio (b)/(a) by weight of 10/90 - 30/70 and F is methylene or a mixture of methylene and $-\text{CH}_2\text{OCH}_2-$. Desirably, F consists of 100 mol% of methylene or 90 mol% or more, preferably 95 mol% or more, of methylene. Depending upon the use,

F may contain 20-30 mol% of $-\text{CH}_2\text{OCH}_2-$.

The symbol n is a number in the range of 1-100, preferably 2-20 on an average. The number average molecular weight preferably falls in the range of 300-1,000 while the weight average molecular weight falls in the range of 500-2,000. The ratio of the latter to the former is in the range of 1.5-3. The aromatic oligomer or the aromatic oligomer resin preferably exhibits a softening point in the range of 50-180 °C, preferably in the range of 70-160 °C. Odor may emanate when the softening point is too low and the compatibility and adhesive property deteriorate when the softening point is too high. The aromatic oligomer resin which comprises the aromatic oligomer as the principal component is obtained when a monocyclic or tricyclic or higher compound is used as an aromatic compound in a small amount together with a bicyclic or tricyclic aromatic compound or when the reaction conditions are changed so that compounds other than the one represented by formula (1) form in a small amount.

Examination of the aromatic oligomer indicated that high-temperature treatment with oxalic acid used as a catalyst causes nearly complete escape of oxygen originating in formaldehyde compound out of the system and that the reaction carried out under mild conditions in the presence of sulfuric acid as a catalyst allows oxygen originating in formaldehyde or a derivative thereof to remain in the system. This is probably due the difference in the mode of linkage of aromatic rings, via the methylene linkage in the former vs. via the ether linkage such as $-\text{CH}_2\text{OCH}_2-$ in the latter. It is desirable for the aromatic oligomer of this invention to contain 3 wt% or less, preferably 1 wt% or less, of oxygen originating in the ether linkage and 20 wt% or less, preferably 15 wt% or less, of total oxygen including oxygen originating in phenols such as alkylphenols.

The aromatic oligomer of this invention or the aromatic oligomer resin which comprises said aromatic oligomer as the principal component performs well not only as a tackifier but also as a vibration damping agent. However, in order to extract better performance as a vibration damping agent, it is preferable to design aromatic oligomers in the following manner.

Although an aromatic oligomer of this type can be obtained from an aromatic compound, a phenol and formaldehyde or a derivative thereof as reactants, a preferred raw material aromatic compound is the one mainly comprised of 1 or 2 kinds of bicyclic aromatic compounds selected from naphthalene and benzothiophene and such a raw material may be comprised of only one of

naphthalene and benzothiophene, of only the two or of the two mixed with a small amount of other aromatic compounds.

The aforementioned other aromatic compounds include methylnaphthalene, dimethylnaphthalene, acenaphthene, fluorene, anthracene and phenanthrene, preferably bicyclic aromatic compounds such as methylnaphthalene and dimethylnaphthalene. An advantageous proportion of an aromatic compound and a phenol in order to obtain the resin represented by formula (1) is 30-90%, preferably 60-80%, of the sum of polycyclic aromatic compounds naphthalene and benzothiophene, 20-40% of phenols, and possibly a small amount of other aromatic compounds such as methylnaphthalene. The proportion of naphthalene and benzothiophene in the polycyclic aromatic compounds is 10-100%, preferably 30-97%, of the former and 0-100%, preferably 10-70%, of the latter.

Aromatic hydrocarbon oil containing 90% or more of naphthalene or aromatic oil containing 10% or more of benzothiophene may be either a material of high purity or aromatic hydrocarbon oil containing the two as principal components. Available as such aromatic hydrocarbon oil are fractions of coal tar corresponding to naphthalene oil, methylnaphthalene oil and middle oil, the intermediate products obtained by recovering the principal components from these fractions by such means as distillation and the residual oil.

Aromatic hydrocarbon oil containing 90% or more of naphthalene may be refined naphthalene, but a preferred example is 95% grade naphthalene which contains other components such as benzothiophene and methylnaphthalene.

Aromatic oil containing 10% or more of benzothiophene is preferably a material containing 30% or more of benzothiophene, 30% or more of aromatic hydrocarbons and 25% or more of naphthalene. A preferred example is oil formed as byproduct in refining crude naphthalene; benzothiophene is concentrated to 10-50% while naphthalene is decreased to 70-40% in the oil.

The kind and proportion of a phenol and formaldehyde or a derivative thereof are as described earlier. The same holds for the catalyst and reaction conditions. The polycyclic aromatic compounds perform the functions of improving vibration damping property, adequately controlling the polarity of aromatic oligomer and enhancing the compatibility with SBR and other resins and rubbers or with solvents.

The aromatic oligomer obtained in this manner is the aromatic oligomer represented by the aforementioned formula (1) or the aromatic oligomer resin which comprises said aromatic oligomer as the principal component. The number

average molecular weight of the aromatic oligomer or the aromatic oligomer resin is preferably in the range of 300-1,000, the weight average molecular weight is in the range of 500-2,000 and the ratio of the latter to the former is in the range of 1.5-3. The aromatic oligomer or the aromatic oligomer resin desirably exhibits a softening point in the range of 50-180°C, preferably 70-160 °C. In case the softening point is too low or too high, the temperature range exhibiting good vibration damping property deviates from the range in common use and the compatibility deteriorates.

Brief Description of the Drawings

Figs. 1 and 2 are graphs illustrating the relationship between $\tan \delta$ and temperature obtained when the aromatic oligomer of this invention is used as a vibration damping agent.

Preferred Embodiments of the Invention

The aromatic oligomer of this invention (including the aromatic oligomer resin which comprises said aromatic oligomer as the principal component) can be used as a tackifier singly or together with known tackifiers and other additives. For example, the aromatic oligomer is incorporated as a tackifier in hot-melt adhesives based on rubbers such as SBR, hot-melt adhesives based on vinyl acetate polymers and other vinyl polymers, acrylic pressure sensitive adhesives, emulsion adhesives, curing adhesives based on epoxy resins and coatings for the purpose of providing or improving adhesive property. Advantageously, it is incorporated in adhesives based on rubber such as SBR. In this case, synthetic rubber such as chloroprene and SBR, natural rubber and modifications of these rubbers by such means as hydrogenation can be used as base rubber and, in addition, stabilizers, lubricants, fillers and softeners may be incorporated in the adhesives. The proportion of the aromatic oligomer as a tackifier is 50-400 parts by weight, preferably 100-300 parts by weight, per 100 parts by weight of the base rubber or resin.

The aromatic oligomer of this invention can also be used as a vibration damping agent. In this case, the aforementioned aromatic oligomer may be used as it is or after refining or fractionation by molecular weight. The aromatic oligomer of this invention as a vibration damping agent is incorporated in a

vibration damping material such as resin, rubber and bitumen. In this case, it is allowable to add, together with the vibration damping agent of this invention, other known vibration damping agents, fillers such as carbon black, calcium carbonate, titanium oxide, clay, talc, mica and alumina, process oil, antioxidants and other additives.

Advantageously, the aromatic oligomer of this invention as a vibration damping agent is incorporated in rubber such as SBR, butyl rubber, natural rubber, diene rubber, chloroprene and a modification thereof by hydrogenation or in elastic resin such as EVA (ethylene-vinyl acetate copolymer) in an amount of 10-70%, preferably 30-60%. The use of the aromatic oligomer of this invention as a vibration damping agent in plural combinations can provide good vibration damping property in a wider temperature range. When used in combination with another vibration damping agent, the aromatic oligomer of this invention can remedy the defect of the other vibration damping agent.

This invention is described below with reference to the examples in which % and part are on a weight basis.

Example 1

In a flask were placed 134 parts of coal-based 95% naphthalene (sulfur content, 5,000 ppm), 68 parts of p-tert-butylphenol and 34 parts of 98% paraformaldehyde, the contents were kept at 110 °C and 22 parts of oxalic acid was added. The mixture was allowed to react at 130 °C with stirring for 2.5 hours to produce an oligomer. The low-boiling substances such as water formed in the reaction were refluxed. Upon completion of the reaction, a condenser was attached to the flask and the mixture was distilled at normal pressure initially. The low-boiling substances such as water and formaldehyde distilled by the time the temperature reached 200°C. Thereafter, the distillation was carried out at a reduced pressure of 100 mmHg while raising the temperature from 200 °C to 270 °C to collect a naphthalene fraction. The naphthalene fraction amounted to 100 parts and showed a purity of 99.9% or more. From the flask was obtained 120 parts of oligomer A exhibiting a softening point of 113.6°C, a number average molecular weight of 548 and a weight average molecular weight of 1,459.

Example 2

In a flask were placed 176 parts of a mixture of coal-based methylnaphthalenes (sulfur content, 5,200 ppm), 80 parts of p-tert-butylphenol

and 44 parts of 98% paraformaldehyde, the contents were kept at 110 °C and 23 parts of oxalic acid was added. The mixture was allowed to react at 130 °C with stirring for 2.5 hours to produce an oligomer. The low-boiling substances such as water formed in the reaction were refluxed. Upon completion of the reaction, a condenser was attached to the flask and the mixture was distilled at normal pressure initially. The low-boiling substances such as water and formaldehyde distilled by the time the temperature reached 200 °C . Thereafter, the distillation was carried out at a reduced pressure of 100 mmHg while raising the temperature from 200 °C to 270 °C to collect a methylnaphthalene fraction which amounted to 131 parts. From the flask was obtained 139 parts of oligomer B exhibiting a softening point of 140.7 °C.

Example 3

In a flask were placed 310 parts of a coal-based mixture containing anthracene (sulfur content, 6,000 ppm), 106 parts of p-tert-butylphenol and 52 parts of 98% paraformaldehyde, the contents were kept at 110°C and 28 parts of oxalic acid was added. The mixture was allowed to react at 130 °C with stirring for 2.5 hours to produce an oligomer. The low-boiling substances such as water formed in the reaction were refluxed. Upon completion of the reaction, a condenser was attached to the flask and the mixture was distilled at normal pressure initially. The low-boiling substances such as water and formaldehyde distilled by the time the temperature reached 200 °C . Thereafter, the distillation was carried out at a reduced pressure of 100 mmHg while raising the temperature from 200 °C to 280 °C to collect an anthracene fraction which amounted to 191 parts. From the flask was obtained 235 parts of oligomer C exhibiting a softening point of 105.0 °C.

As in Examples 1-3, oligomers D-H were prepared by changing the kind of aromatic compound and phenol. The results are shown in Table 1. In the table, the symbols mean the following: N, naphthalene; MN, methylnaphthalene; AN, anthracene; mixed oil, a fraction of aromatic oil containing the prefixed aromatic compound as the principal component; Ph, phenol; PTBP, para-tert-butylphenol; Mn , number average molecular weight; Mw, weight average molecular weight. The oxygen content (wt%) is obtained from elemental analysis and it is 5.4 for oligomer A in Example 1, 6.2 for oligomer B in Example 2 and 4.8 for oligomer C in Example 3.

Table 1

Oligomer	Aromatic compound	Phenol	Catalyst	Mn	Mw	Softening point °C	Oxygen content wt%
D	N	none	sulfuric acid	407	993	75.7	13.0
E	N	P h	sulfuric acid	461	916	92.6	5.9
F	α - MN	P h	sulfuric acid	399	742	78.3	4.8
G	MN mixed oil	PTBP	Oxalic acid	654	1498	120	5.2
H	AN mixed oil	PTBP	Oxalic acid	499	1423	156	3.8

Example 4

A resin composition formulated from each of oligomers A-C obtained in Examples 1-3 by adding 20% or 50% of the oligomer to SBR was inserted between two plates of SUS304 (conforming to JIS G4305) measuring 150 × 25 × 1.5 mm in such a manner as to provide an adhesive area of 10 × 25 mm, heated preliminarily at 175°C for 2 minutes and pressed at 50 kgf/cm² for 1 minute to prepare a test sample. Each sample was tested for tensile shear adhesive strength with the use of Shimadzu Autograph AGS-500A. No offensive odor originating in the oligomer was perceived during the preparation of each test sample.

Comparative Example 1

For comparison, SBR alone was tested for tensile shear adhesive strength in the same manner as in Example 1.

Comparative Example 2

A resin composition formulated by adding 50% of commercial xylene resin (HP-120 available from Mitsubishi Gas Chemical Co., Inc.) was tested for tensile shear adhesive strength in the same manner as in Example 1.

The results are summarized in Table 2.

Table 2

Oligomer	Principal aromatic compound	Adhesive strength (kgf/cm ²)
A	Naphthalene	8.0
B	Methylnaphthalene	7.5
C	Anthracene	7.0
none	—	1.6
HP-120	xylene	4.5

Example 5

In a flask were placed 135 parts of coal-based crude naphthalene (naphthalene content, 96%), 68 parts of p-tert-butylphenol and 37 parts of 92% paraformaldehyde, the contents were kept at 110°C and 23 parts of oxalic acid was added. The mixture was allowed to react at 130 °C with stirring for 2.5 hours to produce an oligomer. The low-boiling substances such as water formed in the reaction were refluxed.

Upon completion of the reaction, a condenser was attached to the flask and the mixture was distilled at normal pressure initially. The low-boiling substances such as water and formaldehyde distilled by the time the temperature reached 200 °C. Thereafter, the distillation was carried out at a reduced pressure of 50 mmHg while raising the temperature from 200°C to 270 °C to collect a fraction containing the unreacted raw materials. The fraction amounted to 66 parts. The resin remaining in the flask was an aromatic oligomer (oligomer J) amounting to 120 parts and exhibiting a softening point of 110 °C.

A THF solution was prepared from a 1:1 mixture by weight of oligomer J and EVA (Evaflex 220 available from DuPont- Mitsui Polychemical Co., Ltd.). Small springs (5 mm in outer diameter and 29 mm in length) were impregnated with the solution and dried at room temperature for 24 hours to form a film in which the interstices between the springs were filled with a mixture of the resin and rubber materials. The film was used as the sample for evaluating vibration damping characteristics by DSA (Dynamic Spring Analysis).

The kinematic viscosity of sample 1 prepared in this manner was determined by a measuring instrument (RHEOBIBRON DDV-II-EP, a product of Orientec Corp.) in the temperature range of -110°C to 150 °C and the results are shown in Fig. 1 as a plot of $\tan \delta$ against temperature.

Example 6

In a flask were placed 135 parts of the oil (containing 40% of benzothiophene and 57% of naphthalene) remaining after refining coal-based crude naphthalene by crystallization and separating refined naphthalene, 68 parts of p-tert-butylphenol and 37 parts of 92% paraformaldehyde, the contents were kept at 110°C and 23 parts of oxalic acid was added. The mixture was allowed to react at 130 °C with stirring for 2.5 hours to produce an oligomer. The low-boiling substances such as water formed in the reaction were refluxed.

Upon completion of the reaction, a condenser was attached to the flask and the mixture was distilled at normal pressure initially. The low-boiling substances such as water and formaldehyde distilled by the time the temperature reached 200 °C. Thereafter, the distillation was carried out at a reduced pressure of 50 mmHg while raising the temperature from 200°C to 270 °C to collect a fraction containing the unreacted raw materials. The fraction amounted to 66 parts. The resin remaining in the flask was an aromatic oligomer (oligomer K) amounting to 151 parts and exhibiting a softening point of 126 °C.

A 1:1 mixture by weight of oligomer K and EVA (Evaflex 220 available from Mitsui-DuPont Polychemical Co., Ltd.) was processed as in Example 1 to prepare sample 2 for evaluating the vibration damping characteristics and the kinematic viscosity was determined in the temperature range of -110 °C to 150 °C. The results are shown in Fig. 1 as a plot of $\tan \delta$ against temperature.

The oxygen content of aromatic oligomer J in Example 5 was 5.4 wt% and that of aromatic oligomer K in Example 6 was 4.8 wt%.

Example 7

A 1:1 mixture by weight of aromatic oligomer J obtained in Example 5 and SBR (Tufprene A available from Asahi Chemical Industry Co., Ltd.) was processed as in Example 1 to prepare sample 3 for evaluating the vibration damping characteristics and the kinematic viscosity was determined in the temperature range of -110°C to 150 °C. The results are shown in Fig. 2 as a plot of $\tan \delta$ against temperature.

Comparative Example 3

Sample 4 for evaluating the vibration damping characteristics was prepared as in Example 1 except using a THF solution of EVA (Evaflex 220 available from Mitsui-DuPont Polychemical Co., Ltd.) and no aromatic oligomer and the kinematic

viscosity was determined in the temperature range of -110°C to 150°C . The results are shown in Fig. 1 as a plot of $\tan \delta$ against temperature.

Comparative Example 4

Sample 5 for evaluating the vibration damping characteristics was prepared as in Example 1 except using a THF solution of SBR (Tufprene A available from Asahi Chemical Industry Co., Ltd.) and no aromatic oligomer and the kinematic viscosity was determined in the temperature range of -110°C to 150°C . The results are shown in Fig. 2 as a plot of $\tan \delta$ against temperature.

As is shown in Fig. 1, sample 4 of Comparative Example 3 containing EVA alone exhibits a gently sloping peak of $\tan \delta$ equal to 0.120 between -5.2°C and 16.8°C . On the other hand, sample 1 containing aromatic oligomer J of Example 5 exhibits a sharp peak of $\tan \delta$ equal to 0.530 at 40.6°C and this is a proof that the sample is provided with vibration damping property.

Sample 2 containing aromatic oligomer K of Example 6 exhibits peaks of $\tan \delta$, one equal to 0.245 at 62.6°C and another equal to 0.409 at 175°C , and the sample is expected to manifest vibration damping property in a higher temperature range.

Thus, it is possible to control the temperature range of vibration damping performance by selecting an adequate aromatic oligomer of this invention.

As shown in Fig. 2, sample 5 of Comparative Example 4 containing SBR alone exhibits a small $\tan \delta$ peak equal to 0.050 at -75.4°C and a large $\tan \delta$ peak equal to 0.405 at 96.5°C .

On the other hand, sample 3 of Example 7 containing aromatic oligomer J exhibits a $\tan \delta$ peak equal to 0.575 at 100.5°C and the sample apparently shows improved vibration damping property at this temperature.

Thus, it is possible to control the temperature range of vibration damping performance by selecting an adequate polycyclic aromatic oligomer.

Industrial Applicability

The aromatic oligomer of this invention is odorless and hence valuable in respect of use environment. It is also suitable for use as a tackifier for hot-melt adhesives. Moreover, it can give good vibration damping property. It can be prepared with relative ease. When used singly or in combination with others, it manifests good vibration damping performance in a wide temperature range.

What is claimed is:


1. An aromatic oligomer represented by the following formula (1);

$$(A - F)_n - A \quad (1)$$

wherein A is a unit comprising (a) 30-90 wt% of a bicyclic or tricyclic aromatic compound and (b) 10-70 wt% of a phenol compound, F is methylene or a mixture of methylene and $-CH_2OCH_2-$ and n is a number of 1-100.
2. An aromatic oligomer as described in claim 1 wherein the oxygen content is 20% or less.
3. An aromatic oligomer resin which comprises the aromatic oligomer described in claim 1 as the principal component.
4. An aromatic oligomer as described in claim 1 which is obtained by the reaction of one kind or two kinds or more of aromatic compounds selected from naphthalene, methylnaphthalene, dimethylnaphthalene, acenaphthene, fluorene, anthracene, phenanthrene, pyrene, benzothiophene and fluoranthene, one kind or two kinds or more of phenols selected from phenol and alkylphenols and one kind or two kinds of more of formaldehyde compound selected from formalin, formaldehyde and paraformaldehyde and exhibits a softening point of 50-180 °C.
5. A tackifier which comprises the aromatic oligomer described in claim 1 as an active ingredient.
6. A vibration damping agent which comprises the aromatic oligomer described in claim 1 as an active ingredient.

Abstract

This invention relates to an aromatic oligomer represented by the following formula (1):



wherein A is a unit comprising (a) 30-90 wt% of a bicyclic or tricyclic aromatic compound and (b) 10-70 wt% of a phenol, F is methylene or a mixture of methylene and $-\text{CH}_2\text{OCH}_2-$ and n is a number of 1-100. The aromatic oligomer is obtained by the reaction of a polycyclic aromatic compound such as naphthalene and benzothiophene, a phenol and formaldehyde compound in the presence of an acid catalyst. The aromatic oligomer is odorless and useful for various applications. In particular, when incorporated in rubber or resin, the aromatic oligomer can perform excellently as a tackifier in a wide temperature range or perform excellently as a vibration damping agent.

Fig. 1





Fig. 2



BIRCH, STEWART, KOLASCH & BIRCH, LLP

PLEASE NOTE:
YOU MUST
COMPLETE THE
FOLLOWING:

COMBINED DECLARATION AND POWER OF ATTORNEY
FOR PATENT AND DESIGN APPLICATIONS

ATTORNEY DOCKET NO
1752-0155P

As a below named inventor, I hereby declare that: my residence, post office address and citizenship are as stated next to my name; that I verily believe that I am the original, first and sole inventor (if only one inventor is named below) or an original, first and joint inventor (if plural inventors are named below) of the subject matter which is claimed and for which a patent is sought on the invention entitled:

Insert Title: **Aromatic Oligomer and Use Thereof**

Fill in Appropriate
Information -
For Use Without
Specification
Attached:

the specification of which is attached hereto. If not attached hereto,
the specification was filed on _____ as
United States Application Number _____; and /or
the specification was filed on August 30, 2000 as PCT
International Application Number PCT/JP00/05881; and was
amended under PCT Article 19 on _____ (if applicable)

I hereby state that I have reviewed and understand the contents of the above identified specification, including the claims, as amended by any amendment referred to above.

I acknowledge the duty to disclose information which is material to patentability as defined in Title 37, Code of Federal Regulations, §1.56.

I do not know and do not believe the same was ever known or used in the United States of America before my or our invention thereof, or patented or described in any printed publication in any country before my or our invention thereof or more than one year prior to this application, that the same was not in public use or on sale in the United States of America more than one year prior to this application, that the invention has not been patented or made the subject of an inventor's certificate issued before the date of this application in any country foreign to the United States of America on an application filed by me or my legal representatives or assigns more than twelve months (six months for designs) prior to this application, and that no application for patent or inventor's certificate on this invention has been filed in any country foreign to the United States of America prior to this application by me or my legal representatives or assigns, except as follows.

I hereby claim foreign priority benefits under Title 35, United States Code, §119 (a)-(d) of any foreign application(s) for patent or inventor's certificate listed below and have also identified below any foreign application for patent or inventor's certificate having a filing date before that of the application on which priority is claimed:

Insert Priority
Information:
(if appropriate)

Prior Foreign Application(s)			Priority Claimed	
<u>244432/1999</u> (Number)	<u>Japan</u> (Country)	<u>08/31/1999</u> (Month/Day/Year Filed)	<input checked="" type="checkbox"/> Yes	<input type="checkbox"/> No
<u>200630/2000</u> (Number)	<u>Japan</u> (Country)	<u>07/03/2000</u> (Month/Day/Year Filed)	<input checked="" type="checkbox"/> Yes	<input type="checkbox"/> No
_____ (Number)	_____ (Country)	_____ (Month/Day/Year Filed)	<input type="checkbox"/> Yes	<input type="checkbox"/> No
_____ (Number)	_____ (Country)	_____ (Month/Day/Year Filed)	<input type="checkbox"/> Yes	<input type="checkbox"/> No
_____ (Number)	_____ (Country)	_____ (Month/Day/Year Filed)	<input type="checkbox"/> Yes	<input type="checkbox"/> No

I hereby claim the benefit under Title 35, United States Code, §119(e) of any United States provisional application(s) listed below.

Insert Provisional
Application(s):
(if any)

_____ (Application Number)	_____ (Filing Date)
_____ (Application Number)	_____ (Filing Date)

All Foreign Applications, if any, for any Patent or Inventor's Certificate Filed More Than 12 Months (6 Months for Designs) Prior To The Filing Date of This Application:

Insert Requested
Information:
(if appropriate)

Country	Application No	Date of Filing (Month/Day/Year)
_____	_____	_____
_____	_____	_____

I hereby claim the benefit under Title 35, United States Code, §120 of any United States application(s) listed below and, insofar as the subject matter of each of the claims of this application is not disclosed in the prior United States application in the manner provided by the first paragraph of Title 35, United States Code, §112, I acknowledge the duty to disclose information which is material to patentability as defined in Title 37, Code of Federal Regulations, §1.56 which became available between the filing date of the prior application and the national or PCT international filing date of this application:

Insert Prior U.S.
Application(s):
(if any)

_____ (Application Number)	_____ (Filing Date)	_____ (Status - patented, pending, abandoned)
_____ (Application Number)	_____ (Filing Date)	_____ (Status - patented, pending, abandoned)

I hereby appoint the following attorneys to prosecute this application and/or an international application based on this application and to transact all business in the Patent and Trademark Office connected therewith and in connection with the resulting patent based on instructions received from the entity who first sent the application papers to the attorneys identified below, unless the inventor(s) or assignee provides said attorneys with a written notice to the contrary:

15-
Terrell C. Birch (Reg. No. 19,382)
Joseph A. Kolasch (Reg. No. 22,463)
Bernard L. Sweeney (Reg. No. 24,448)
Charles Gorenstein (Reg. No. 29,271)
Leonard R. Svensson (Reg. No. 30,330)
Andrew D. Meikle (Reg. No. 32,868)
Joe McKinney Muncy (Reg. No. 32,334)
C. Joseph Faraci (Reg. No. 32,350)

Raymond C. Stewart (Reg. No. 21,066)
James M. Slattery (Reg. No. 28,380)
Michael K. Mutter (Reg. No. 29,680)
Gerald M. Murphy, Jr. (Reg. No. 28,977)
Terry L. Clark (Reg. No. 32,644)
Marc S. Weiner (Reg. No. 32,181)
Donald J. Daley (Reg. No. 34,313)

Send Correspondence to:

BIRCH, STEWART, KOLASCH & BIRCH, LLP

P.O. Box 747 • Falls Church, Virginia 22040-0747

Telephone: (703) 205-8000 • Facsimile: (703) 205-8050

PLEASE NOTE:
YOU MUST
COMPLETE THE
FOLLOWING:

I hereby declare that all statements made herein of my own knowledge are true and that all statements made on information and belief are believed to be true; and further that these statements were made with the knowledge that willful false statements and the like so made are punishable by fine or imprisonment, or both, under Section 1001 of Title 18 of the United States Code and that such willful false statements may jeopardize the validity of the application or any patent issued thereon.

Full Name of First or Sole
Inventor:
Insert Name of Inventor
Insert Date This
Document is Signed

Insert Residence
Insert Citizenship

Insert Post Office
Address

Full Name of Second
Inventor, if any:

see above

Full Name of Third
Inventor, if any

see above

Full Name of Fourth
Inventor, if any

see above

Full Name of Fifth
Inventor, if any

see above

GIVEN NAME <u>Toshihide</u>	FAMILY NAME <u>SENZAKI</u>	INVENTOR'S SIGNATURE <u>千崎利英</u>	DATE <u>February 12, 2002</u>
Residence (City, State & Country) <u>Kitakyushu-shi, Fukuoka Japan JPX</u>		CITIZENSHIP <u>Japanese</u>	
POST OFFICE ADDRESS (Complete Street Address including City, State & Country) <u>c/o Research&Development Laboratories, Nippon Steel Chemical Co., Ltd , 46-80, Sakinohama, Oaza Nakabaru, Tobata-ku, Kitakyushu-shi, Fukuoka 804-8503 Japan</u>			
GIVEN NAME <u>Takahiro</u>	FAMILY NAME <u>IMAMURA</u>	INVENTOR'S SIGNATURE <u>今村高弘</u>	DATE <u>February 12, 2002</u>
Residence (City, State & Country) <u>Kitakyushu-shi, Fukuoka Japan JPX</u>		CITIZENSHIP <u>Japanese</u>	
POST OFFICE ADDRESS (Complete Street Address including City, State & Country) <u>c/o Research&Development Laboratories, Nippon Steel Chemical Co , Ltd , 46-80, Sakinohama, Oaza Nakabaru, Tobata-ku, Kitakyushu-shi, Fukuoka 804-8503 Japan</u>			
GIVEN NAME	FAMILY NAME	INVENTOR'S SIGNATURE	DATE
Residence (City, State & Country)		CITIZENSHIP	
POST OFFICE ADDRESS (Complete Street Address including City, State & Country)			
GIVEN NAME	FAMILY NAME	INVENTOR'S SIGNATURE	DATE
Residence (City, State & Country)		CITIZENSHIP	
POST OFFICE ADDRESS (Complete Street Address including City, State & Country)			
GIVEN NAME	FAMILY NAME	INVENTOR'S SIGNATURE	DATE
Residence (City, State & Country)		CITIZENSHIP	
POST OFFICE ADDRESS (Complete Street Address including City, State & Country)			